

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08G 73/02, D21H 17/55, 21/20	A1	(11) International Publication Number: WO 99/06469 (43) International Publication Date: 11 February 1999 (11.02.99)
(21) International Application Number: PCT/US98/16249 (22) International Filing Date: 28 July 1998 (28.07.98) (30) Priority Data: 08/901,887 29 July 1997 (29.07.97) US (71) Applicant: HERCULES INCORPORATED [US/US]; Intellectual Property Section, 1313 N. Market Street, Wilmington, DE 19894-0001 (US). (72) Inventor: BOWER, Barton, K.; 220 Brabson Road, Kirks Mill, Nottingham, PA 19362 (US). (74) Agent: SZANTO, Ivan, G.; Intellectual Property Section, Hercules Plaza, 1313 N. Market Street, Wilmington, DE 19894-0001 (US).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, HR, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: POLYAMIDOAMINE/EPICHLOROHYDRIN RESINS BEARING POLYOL SIDECHAINS AS DRY STRENGTH AGENTS (57) Abstract Compositions suitable for use as dry strength additives comprising water soluble polyamidoamine/epichlorohydrin resin bearing polyol sidechains wherein the weight fraction of the polyol in the resin is less than 50 percent by weight and the polyol sidechain is attached to the polyamidoamine/epichlorohydrin resin by carbon-nitrogen bond, such as amide bond or secondary or tertiary amine bonds.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

Bower Case 10

**Polyamidoamine/Epichlorohydrin Resins Bearing
Polyol Sidechains as Dry Strength Agents**

Background of the Invention

5 Field of the Invention

The present invention relates to dry strength additives for paper and more particularly it relates to polyamidoamine/epichlorohydrin resins bearing polyol sidechains.

10

Description of the Prior Art

Strength is a very important property of paper products. At constant basis weight, the use of dry strength additives increases strength. Dry strength agents enable the papermaker to use less pulp, less expensive pulp and/or more filler while making sufficiently strong, stiff and opaque paper products. Benefits to the users of paper products include stronger packaging and lower shipping or postage costs. Conventional dry strength agents include starch, urea/formaldehyde resins, melamine/formaldehyde resins, acrylamide copolymers and polyamidoamine/epichlorohydrin resins.

USP 3,962,159 (Ray-Chaudhuri, et al.) discloses copolymerization of water dispersible starches, polyamidoamines and epichlorohydrin. The weight ratio of starch to polyamidoamine is between 1:9 and 9:1. While Ray-Chaudhuri uses the term "graft copolymer" in fact he is making block copolymers of the polyamidoamines and starch using epichlorohydrin as a

- 2 -

condensing agent. All USP 3,962,159 preparations form carbon-oxygen bonds between the starch and the polyamidoamine except for the one in Example 19 where a quaternary ammonium bond is formed.

5 **USP 3,314,897 (Gaertner)** discloses treating polysaccharide substrates (starch, textiles, such as cotton, linen, rayon, and cellulose paper products) with a minor amount of a prepolymer composed of aliphatic amine/epichlorohydrin adduct reacted with an
10 amine having at least 2 amino hydrogens. In other words Gaertner uses a minor amount of his prepolymer to modify the polysaccharide substrates instead of modifying a polyamidoamine/epichlorohydrin resin by including polyol sidechains and obtaining a water
15 soluble product.

USP 3,320,066 (Garth) discloses the separate addition of polyamide-epichlorohydrin resin, dialdehyde carbohydrate and optionally carboxymethyl cellulose and/or cationic starch to paper pulp, i.e., to the
20 dilute slurry of paper pulp obtained after the beating operation.

South African Patent 695018 discloses starch/polymeric polyamine compositions wherein the polyamine is formed by a reaction of an alkylene
25 dihalide, e.g. ethylene dichloride, and an amine, e.g., diethylenetriamine. There is no disclosure of making a

- 3 -

polyaminoamide or a polyaminoamide/epichlorohydrin resin.

French Patent 1,488,141 (which corresponds to Canadian patent 797,130) discloses improving the strength of cellulosic material by (a) treating an aqueous suspension of cellulose fibers with a cationic wet strength resin (such as cationic urea-formaldehyde resin, and cationic polyamides, obtained from the reaction of polyalkylenepolyamine and dicarboxylic acid which are crosslinked with epichlorohydrin) (b) adjusting the pH of the suspension to 4.0-5.5, (c) treating the suspension with a dialdehyde polysaccharide, (d) adjusting the pH of the suspension to 4.0-5.5 and (e) forming a web from the treated cellulose fibers.

USP 4,097,427 (Aitken) discloses the interaction of polyalkylenepolyamine/epichlorohydrin resins with starch for improved wet strength. It does not disclose polyamidoamine/epichlorohydrin resins.

USP 3,763,060 (Hamerstrand et al.) discloses the interaction of sodium starch xanthate with polyamide polyamine-epichlorohydrin (PAE) resin wherein the bond between the starch xanthate and the PAE resin is a carbon-sulphur bond.

USP 4,940,514 (Stange, et al.) discloses the interaction of vinyl polymers with enzymatically

- 4 -

digested starch. There is no disclosure of polyamidoamine/ epichlorohydrin resins.

USP 4,818,341 (Degen, et al.) discloses the interaction of vinyl polymers with enzymatically
5 digested starch. There is no disclosure of polyamidoamine/epichlorohydrin resins.

USP 5,334,287 (Hartmann, et al.) discloses the use of N-vinylcarboxamide free radical graft copolymers of mono-, oligo- or poly-saccharides. It does not
10 disclose polyamidoamine/epichlorohydrin resins.

Summary of the Invention

According to the present invention there are provided compositions for improving the dry strength of paper comprising water-soluble, azetidinium ion-
15 containing polyamidoamine/epichlorohydrin resins bearing polyol sidechains wherein the weight fraction of the polyol in the resin is less than 50% by weight and the polyol sidechain is attached to the
polyamidoamine/epichlorohydrin resin by a carbon-
20 nitrogen bond.

According to the present invention there are provided processes for the preparation of the water-soluble polyamidoamine/epichlorohydrin resins bearing polyol sidechains.

25 According to the present invention there is

- 5 -

provided paper having improved dry strength characteristics containing water soluble polyamidoamine/epichlorohydrin resins bearing polyol sidechains.

5 According to the present invention there is further provided the process to enhance the dry strength of paper by adding to the aqueous pulp the water-soluble polyamidoamine/epichlorohydrin resins bearing polyol sidechains.

10 Detailed Description of the Invention

 It has been discovered that water-soluble, azetidinium ion-containing polyamidoamine/epichlorohydrin resins bearing polyol sidechains, wherein the weight fraction of the polyol in the resin is less than
15 50% by weight and the polyol sidechain is attached to the polyamidoamine/epichlorohydrin resin by amide, secondary amine or tertiary amine carbon-nitrogen bonds, will improve the dry strength of paper and as such will have an economic benefit for both the
20 papermaker and the paper user.

 The polyamidoamines are prepared by the method described in US 2,926,116 and EPA 488,767. Polyamidoamine/epichlorohydrin resins having aminochlorohydrin, azetidinium and/or epoxide
25 functionality may be prepared as described in US 2,926,116; US 5,171,795; EPA 488,767; GB 865,727; US

- 6 -

4,605,709; and US 4,537,657. The disclosure of these patents is incorporated herein by reference.

Polyol sidechains are defined as organic residues containing two or more hydroxyl groups, wherein at least half of the carbon atoms in the polyol sidechain bear hydroxyl groups. In order to be useful as starting materials for the compositions of the present invention, the precursor molecule of a polyol sidechain must also have one, and only one, functional group selected from the group consisting of carboxylic acid, lactone, amine and aldehyde. Carbohydrates, including monosaccharides, disaccharides, oligosaccharides and polysaccharides, glycerol, glyceraldehyde, 3-amino-1,2-propanediol, 3-alkylamino-1,2-propanediol, 3-hydroxyethylamino-1,2-propanediol, threose, erythrose, xylose, arabinose, ribose, fructose, glucose, galactose, mannose, sucrose, maltbiose, maltotriose, lactose, cellobiose, hemicellulose, cellulose, starch, dextrin, pyrodextrin, alginate, glycogen, inulin, furcellaran, agar, carrageenan, microbial gum, locust bean gum, fucoidan, guar, laminaran, gum arabic, ghatti gum, karaya gum, tragacanth gum, okra gum, tamarind gum, xanthan, scleroglucan, psyllium gum, pectin, dextran, methylcellulose, ethylcellulose, hydroxyethylcellulose, hydroxypropylcellulose and chitin are polyol sidechain precursors or they may be converted to polyol sidechain precursors. If not already present, a carboxylic acid, lactone, amine or aldehyde functional group can be provided to the

- 7 -

structure of the starting material using conventional synthetic methods. For example, chitin may be depolymerized and deacetylated to form glucosamine, or alginate may be completely decarboxylated to give a
5 terminal monoaldehyde.

Preferred polyol residues are threityl, erythrityl, xylityl, arabinityl, ribityl, fructityl, glucityl, galactityl, mannityl, maltobiotyl, maltotrietyl, lactobiotyl, cellobiotyl and
10 pryrodextrinityl. For example, the term "glucityl polyol residue" refers to the 6-carbon polyol sidechain attached by means of the precursors 1-amino-1-deoxysorbitol, 1-methylamino-1-deoxysorbitol, glucosamine, gluconic acid, gluconolactone or N-
15 aminoethyl gluconamide.

Most preferred polyol residues are glucityl, maltobiotyl, lactobiotyl and pryrodextrinityl.

The new compositions of the present invention can be made by reacting polyols having carboxylic acid or
20 lactone functionality with polyamidoamines (PAA) to form amide bonds followed by reaction with epichlorohydrin. They can also be made by reaction of polyol amines with azetidinium or epoxide groups of the polyamidoamine/epichlorohydrin (PA/E) resins. Further,
25 they can be made by reductive amination of reducing sugars with polyamidoamines followed by reaction with epichlorohydrin.

- 8 -

Accordingly, the compositions of the present invention can be prepared by (a) reacting a polyol having carboxylic acid or lactone functionality with less than about 95 mole percent of the amine groups of a polyamidoamine to form amide bonds. This is followed by (b) reacting the amine groups of the polyamidoamine that have not been utilized to form the amide bonds with epichlorohydrin to provide at least one of aminochlorohydrin, epoxide or azetidinium chloride functionality. The reaction of carboxylic acid and lactone functional groups with amines, as well as the reaction of amines with epichlorohydrin are well known procedures in the art [for example G. Ziegast, B. Pfannemuller, Makromol. Chem. Rap. Comm., 5, 373 (1984)] and can be carried out in conventional manner.

An alternate process for preparing the water-soluble, azetidinium ion-containing polyamidoamine/epichlorohydrin resins bearing polyol sidechains of the present invention is by reacting a polyol having amine functionality with less than about 95 mole percent of the azetidinium or epoxide functional groups of polyamidoamine/epichlorohydrin resin to form secondary or tertiary amine bonds. The reaction of amines with azetidinium or epoxide functional groups is well known in the art [for example N. B. Chapman et al, J. Chem. Soc., 1925 (1959) and V. R. Gaertner, J. Org. Chem., 33, 523 (1968)] and can be carried out by conventional procedures.

- 9 -

In another method for the preparation of the compositions of the present invention, polyol groups can be attached to polyamidoamine/epichlorohydrin resin by reductive amination of the aldehyde groups of
5 reducing sugars by less than about 95 mole percent of the amine groups of the polyamidoamine to form tertiary amine bonds. Thereafter the amine groups of the polyamidoamine that have not been utilized to form the tertiary amine bonds are reacted with epichlorohydrin
10 to provide at least one of aminochlorohydrin, epoxide or azetidinium chloride functionality. Reductive amination of aldehyde groups by amine groups to form amine bonds is well known in the art (for example J. J. Scheibel et al, U.S. 5,500,150, 3/19/96) and can be
15 carried out by conventional procedures.

The new compositions of this invention retain the ability of polyamidoamine/epichlorohydrin polymers to be substantive to paper pulp, which is anionic, at neutral and basic papermaking pH's. Permanent cationic
20 charge due to the azetidinium group is retained since at least 5 mole % of the azetidinium group that would be present in the absence of polyol sidechains is present in the new compositions. The polyol sidechains will also have an attraction for hemicelluloses on the
25 pulp surfaces.

A fundamental problem of PA/E paper strength agents of prior art is that polyamidoamine/epichlorohydrin polymers do not mix optimally with

- 10 -

amorphous cellulose since a given type of polymer solvates itself better than it would be solvated by a dissimilar type of polymer, and since polyamidoamine/epichlorohydrin polymers are quite
5 different in structure from the amorphous cellulose polymers that naturally occur on the surface of paper pulp fibers. The new compositions of the present invention address this deficiency by providing polyamidoamine/epichlorohydrin polymers with polyol
10 substituents that are highly compatible with amorphous cellulose and improve mixing of the strength additive and amorphous cellulose.

Polyol sidechains attached to polyamidoamine/epichlorohydrin polymers will be attracted to cellulose
15 pulp surfaces and contribute to strength by forming hydrogen bonds with cellulose pulp surfaces. In order to facilitate the fiber-fiber bridging aspect of the mechanism of paper strengthening, the new compositions of this invention retain the self-crosslinking property
20 of polyamidoamine/epichlorohydrin resins by possessing at least 5 mole % of the reactive functional groups (aminochlorohydrin, azetidinium and epoxide) that would be present in the absence of polyol sidechains. The polyol sidechain resins can increase in viscosity and
25 molecular weight during paper drying and storage due to azetidinium and epoxide crosslinking reactions. The azetidinium and epoxide groups also form bonds to paper pulp by reacting with nucleophiles of the amorphous cellulose on the surface of paper pulp.

- 11 -

The following Examples are given for the purpose of illustrating the present invention. All parts and percentages are by weight unless otherwise specified.

5

EXAMPLE 1

Preparation of Polyamidoamine Lactobionic Amide:

Lactobionic acid (26.86 g, 75 mmoles) and a polyamidoamine (Polymer 567 wet strength resin available from Hercules Incorporated) made from adipic
10 acid and diethylenetriamine (57.18 g, 300 mmoles amine) in ethylene glycol (84 g) were heated at 130°C for 80 minutes. Amine titration indicated that 24% of starting amine had been converted to carbohydrate amide.

15 Conversion of Polyamidoamine Lactobionic Amide to Resin:

Polyamidoamine lactobionic amide (50% solids in ethylene glycol, 132.36 g, 176 mmoles amine), water (88.16 g), and epichlorohydrin (21.29 g, 230 mmoles)
20 were stirred at 25°C for 18 hr and then stirred and heated at 65°C for 60 minutes. Water (417.7 g) and concentrated sulfuric acid (4.52 g) were added and the reaction mixture was cooled to room temperature giving product having 13.1% solids, pH 2.89, 46 cP Brookfield
25 viscosity, 4520 ppm 1,3-dichloro-2-propanol, 2320 ppm 3-chloropropanediol and 24 wt% polyol in the final product on a dry organic solids basis.

- 12 -

EXAMPLE 2

Reaction of Polyamidoamine/epichlorohydrin Resin
with Glucosamine :

Polyamidoamine/epichlorohydrin resin (Kymene® 557H, wet
5 strength resin available from Hercules Incorporated
12.3% solids, 63 cP Brookfield viscosity, 8200 ppm 1,3-
dichloro-2-propanol, 2200 ppm 3-chloropropanediol,
499.98 g, 200 mmoles azetidinium plus
aminochlorohydrin) and glucosamine hydrochloride (19.07
10 g, 88 mmoles) were mixed and the pH was adjusted to 10
with sodium hydroxide (6 molar). After stirring and
heating at 65°C for 50 minutes with the pH kept at 10,
the reaction mixture was cooled to room temperature and
acidified with concentrated sulfuric acid (10.89 g)
15 giving product having 17.3% solids, pH 2.95, and
Brookfield viscosity of 39 cP. HPLC (High Performance
Liquid Chromatography) indicated that 39% of the
glucosamine charged had reacted. The weight fraction of
polyol in the final product was 20% on a dry organic
20 solids basis.

EXAMPLE 3

Reaction of Polyamidoamine/epichlorohydrin Resin
with Pyrodextrin N-Aminoethyl Amide :

Polyamidoamine/epichlorohydrin resin (Kymene® 557LX wet
25 strength available from Hercules Incorporated, 12.4%
solids, 42 cP Brookfield viscosity, 780 ppm 1,3-
dichloro-2-propanol, 190 ppm 3-chloropropanediol,
720.89 g, 260 mmoles azetidinium plus
aminochlorohydrin) and pyrodextrin N-aminoethyl amide

- 13 -

(ICN Biomedicals Inc. pyrodextrin or Sigma Chemical Company pyrodextrin, oxidized by bromine, dehydrated, reacted with ethylene diamine, 50% solids in ethylene glycol, 59.63 g, 32 mmoles amine) were stirred at 25°C
5 keeping the pH at 9 with sodium hydroxide (6 molar, 109 g) until the Gardner-Holdt viscosity was "D-E" in 5 hours. Concentrated sulfuric acid (9.5 g) was added giving product with 12.7% solids, pH 2.91, Brookfield viscosity of 78 cP, 350 ppm 1,3-dichloro-2-propanol,
10 220 ppm 3-chloropropanediol, and 24 wt% polyol in the final product on a dry organic solids basis.

- 14 -

EXAMPLE 4

Papermaking and Dry Strength Testing:

In Table 1 dry strengths of papers made from the new dry strength agents are compared with dry strengths of paper made with no strength additive (blank). Papers 1-7 contain resins made by the procedure of Example 1, papers 8-15 resins made by the procedure of Example 2, and papers 16-28 resins made by the procedure of Example 3. The paper pulp was a 70:30 mixture of James River Burgess bleached hardwood kraft : Rayonier bleached softwood kraft. Water hardness was 50 ppm, alkalinity was 25 ppm, and pH was 7.6. After beating with a Jones 12-inch double disk refiner, pulp freeness was 430-435 CSF. Dry strength agents of the present invention were added to the wet end of the papermaking machine at the level of 1 wt% vs. dry paper pulp. The paper was dried to 4.0-4.8 wt. % moisture using a 45 lb/linear inch press and seven drying rolls at 150-190°F. The basis weight of the paper was 40 lbs/ream. Oven curing was carried out at 80°C for 0.5 hr. Z-direction (perpendicular to the plane of the paper) tensile strength was used as the measure of dry strength effect. The Z-direction tensile strength was measured by holding the sheet against two platens with double-sided tape and moving the platens away from each other with a CS-163D Digital ZDT Tester until the paper separated.

Table 1

Increase in Dry Z-Dimension Tensile Strength vs. Blank

Paper #	<u>Polyol Precursor</u>	PAA or <u>PAA/E</u>	Carbo- hydrate <u>Wt%</u>	Inc. ZDT vs. <u>Blank</u>
1	Gluconolactone	P567	26%	19.8%
2	Lactobionic lactone	P567	43	25.0
3	Lactobionic lactone	P567	41	40.0
4	Gluconolactone	P567	13	27.4
5	Maltobionic lactone	P567	22	33.0
6	Maltobionic lactone	P567	38	36.0
7	Lactobionic lactone	P567	24	39.5
8	Glucosamine•HCl	K557H	34	21.8
9	Meglumine	K557H	36	30.2
10	Meglumine	K557H	28	37.5
11	Aminosorbitol	K557H	20	28.8
12	Glucosamine•HCl	K557H	34	29.9
13	Glucosamine•HCl	K557H	34	32.0
14	Aminosorbitol	K557H	20	35.5
15	Glucosamine•HCl	K557H	20	34.3
16	N-Aminoethyl ICN II	K557LX	38	50.4
17	N-Aminoethyl ICN I	K557LX	39	50.4
18	N-Aminoethyl Sigma III	K557LX	37	53.1
19	N-Aminoethyl Sigma III	K557LX	25	58.1
20	N-Aminoethyl Sigma I	K557LX	25	57.8
21	N-Aminoethyl maltobionic	K557LX	17	47.5
22	N-Aminoethyl lactobionic	K557LX	27	43.5
23	N-Aminoethyl Sigma I	K557LX	39	57.6
24	N-Aminoethyl lactobionic	K557LX	15	44.1
25	N-Aminoethyl ICN I	K557LX	24	60.2
26	N-Aminoethyl lactobionic	K557LX	15	47.5
27	N-Aminoethyl ICN II	K557LX	24	54.7
28	N-Aminoethyl maltobionic	K557LX	25	48.2

Claims

1. A composition comprising water soluble, azetidinium ion-containing polyamidoamine/epichlorohydrin resin bearing polyol sidechains wherein the weight fraction of the polyol in the resin is less than 50 percent by weight and the polyol sidechain is attached to the polyamidoamine/epichlorohydrin resin by carbon-nitrogen bond.
2. The composition of claim 1 wherein the polyol sidechain is attached to the polyamidoamine/epichlorohydrin resin by amide bond.
3. The composition of claim 1 wherein the polyol sidechain is attached to the polyamidoamine/epichlorohydrin resin by secondary or tertiary amine bond.
4. The composition of claim 1 wherein the polyol sidechain is selected from the group consisting of the polyol residues in monosaccharides, disaccharides, oligosaccharides and polysaccharides.
5. The composition of claim 1 wherein the polyol sidechain is selected from the group consisting of the polyol residues in monosaccharides, disaccharides, oligosaccharides and polysaccharides, glycerol, glyceraldehyde, 3-amino-1,2-propanediol, 3-alkylamino-1,2-propanediol, 3-hydroxyethylamino-1,2-propanediol, threose, erythrose, xylose, arabinose, ribose, fructose, glucose, galactose, mannose, sucrose, maltbiose, maltotriose, lactose, cellobiose, hemicellulose, cellulose, starch, dextrin, pyrodextrin, alginate, glycogen, inulin, furcellaran, agar, carrageenan, microbial gum, locust bean gum, fucoidan, guar, laminaran, gum arabic, ghatti gum,

karaya gum, tragacanth gum, okra gum, tamarind gum, xanthan, scleroglucan, psyllium gum, pectin, dextran, methylcellulose, ethylcellulose, hydroxyethylcellulose, hydroxypropylcellulose and chitin.

6. The composition of claim 5 wherein the polyol sidechain is selected from the group consisting of threityl, erythrityl, xylityl, arabinityl, ribityl, fructityl, glucityl, galactityl, mannityl, maltobiotyl, maltotrietyl, lactobiotyl, cellobiotyl and pyrodextrinyl.

7. The composition of claim 5 wherein the polyol sidechain is derived from polyol starting material having, either in the natural product or provided by synthetic method, functional groups selected from the group consisting of carboxylic acid, lactone, amine and aldehyde groups.

8. The composition of claim 7 wherein the polyol sidechain is derived from the group consisting of gluconolactone, lactobionic acid, lactobionic lactone, maltobionic acid, maltobionic lactone, glucosamine, 1-amino-1-deoxysorbitol, or 1-N-methylamino-1-deoxysorbitol (meglumine), glucose, maltose, and pyrodextrin N-aminoethyl amide.

9. The composition of claim 6 wherein the polyol sidechain is selected from the group consisting of glucityl, maltobiotyl, lactobiotyl and pyrodextrinyl.

10. The composition of claim 5, 8 or 9 wherein the weight fraction of the polyol in the resin is less than about 40 percent by weight.

11. The composition of claim 5, 8 or 9 wherein the weight fraction of the polyol in the resin is less than about 30 percent by weight.

12. The composition of claim 5, 8 or 9 wherein the weight fraction of the polyol in the resin is at least about 5 percent by weight.

13. The composition of claim 5, 8 or 9 wherein the weight fraction of the polyol in the resin is at least about 10 percent by weight.

14. A process for preparing water soluble polyamidoamine/epichlorohydrin resin bearing polyol sidechains comprising:

(a) reacting polyol having carboxylic acid or lactone functional group with less than about 95 mole percent of the amine groups of polyamidoamine by formation of amide bonds; and

(b) reacting amine groups of the polyamidoamine that have not been utilized to form the amide bonds with epichlorohydrin to provide at least one of aminochlorohydrin, epoxide or azetidinium chloride functionalities.

15. A process for preparing water soluble polyamidoamine/epichlorohydrin resin bearing polyol sidechains comprising: reacting polyol having amine functional group with less than about 95 mole percent of the azetidinium or epoxide functional groups of polyamidoamine/epichlorohydrin resin.

16. A process for preparing water soluble polyamidoamine/epichlorohydrin resin bearing polyol sidechains comprising:

(a) reductive amination of the aldehyde groups of reducing sugars by less than about 95 mole percent of the amine groups of polyamidoamine to form tertiary amine bonds; and

(b) reacting amine groups of the polyamidoamine that have not been utilized to form the tertiaryamine bonds with epichlorohydrin to provide at least one of aminochlorohydrin, epoxide or azetidinium chloride functionalities.

17. Paper containing the composition of claim 1.

18. Paper containing the composition of claim 5.

19. Paper containing the composition of claim 6.

20. Paper containing the composition of claim 9.

21. A process for making paper to enhance the dry strength of the paper produced comprising adding to the aqueous pulp finish at the wet end of the papermaking machine the composition of claim 1 and forming paper from the aqueous furnish.

22. A process for making paper to enhance the dry strength of the paper produced comprising adding to the aqueous pulp finish at the wet end of the papermaking machine the composition of claim 5 and forming paper from the aqueous furnish.

23. A process for making paper to enhance the dry strength of the paper produced comprising adding to the aqueous pulp finish at the wet end of the papermaking machine the composition of claim 6 and forming paper from the aqueous furnish.

24. A process for making paper to enhance the dry strength of the paper produced comprising adding to the aqueous pulp finish at the wet end of the papermaking machine the composition of claim 9 and forming paper from the aqueous furnish.

25. The process of claims 21, 22, 23 or 24 wherein the amount of water soluble polyamidoamine/epichlorohydrin resin bearing polyol sidechains is from about 0.1 to about 10 percent based on the weight of dry pulp.

INTERNATIONAL SEARCH REPORT

Int .ional Application No

PCT/US 98/16249

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C08G73/02 D21H17/55 D21H21/20

According to International Patent Classification(IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C08G D21H

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 3 962 159 A (RAY-CHAUDHURI DILIP K ET AL) 8 June 1976 cited in the application see claim 1; example 19 ---	1-25
A	WO 91 09174 A (HENKEL CORP) 27 June 1991 see claim 1 ---	1-25
A	EP 0 000 714 B (WOLFF WALSRÖDE AG) 31 March 1982 see claim 1 ---	1-25
A	WO 94 16007 A (HENKEL CORP) 21 July 1994 see claim 1 ---	1-25
A	US 3 314 897 A (GAERTNER R) 18 April 1967 cited in the application see column 27, line 8 - line 23; claim 1 -----	1-25

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

28 October 1998

Date of mailing of the international search report

04/11/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Hoffmann, K

INTERNATIONAL SEARCH REPORT

Information on patent family members

Int. l. Application No

PCT/US 98/16249

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 3962159 A	08-06-1976	AU 1047476 A	17-02-1977
		BR 7600653 A	31-08-1976
		CA 1051135 A	20-03-1979
		DE 2604036 A	05-08-1976
		FR 2299360 A	27-08-1976
		GB 1489725 A	26-10-1977
		JP 972682 C	28-09-1979
		JP 51102083 A	09-09-1976
		JP 54003778 B	27-02-1979
		NL 7601014 A,C	05-08-1976
		SE 428129 B	06-06-1983
		SE 7601142 A	04-08-1976
WO 9109174 A	27-06-1991	US 5116887 A	26-05-1992
		AU 639971 B	12-08-1993
		AU 6950191 A	18-07-1991
		CA 2070837 A	08-06-1991
		FI 922621 A	05-06-1992
		JP 5503111 T	27-05-1993
		NO 176804 B	20-02-1995
		US 5120773 A	09-06-1992
EP 0000714 B	21-02-1979	DE 2736651 A	15-02-1979
		AT 365681 B	10-02-1982
		AT 587278 A	15-06-1981
		CA 1124963 A	08-06-1982
		EP 0000714 A	21-02-1979
		FI 782461 A,B,	14-02-1979
		JP 54032186 A	09-03-1979
		US 4267059 A	12-05-1981
WO 9416007 A	21-07-1994	JP 8505653 T	18-06-1996
US 3314897 A	18-04-1967	NONE	